










	ASTM TEST	INDUSTRY STANDARD	TEST RESULTS
 DCOF	DCOF Acutest (wet)	≥ 0.42	Honed Finish ≥ 0.50 ≤ 0.60 Rigato Finish ≥ 0.65 ≤ 0.75
 Scale of Hardness	Scratch Test	Range 0-10	≥ 7
 Modulus of Rupture	C648	≥ 250 lbf	≥ 400 lbf
 Freeze-Thaw	C1026	No sample must show alteration to surface.	No evidence of damage.
 Bond Strength	C482	≥ 50 psi	≥ 200 psi
 Water Absorption	C373	Impervious <0.5%	≤ 0.1%
 Scratch Resistance	C1027	No requirement. Range 0-5.	Class 4
 C650	C650	No Requirement. Range E-A	Class A



Chemical Resistance



Stain Resistance

C1378

.....

No Requirement.
Range E-A

.....

Class A